TECHNICAL DATA SHEET

KEIM TURADO 0.3

1. PRODUCT DESCRIPTION

KEIM Turado 0.3 is a universally applicable natural white renovation bonded render for interior and exterior use, based on lime cement. KEIM Turado 0.3 Corresponds to mortar group GP CS III according to DIN EN 998-1.

2. FIELD OF APPLICATION

Mineral fine plaster for flat, finely felted surfaces, e.g. in reveals and flaps on doors and windows as well as in the base area. KEIM Turado 0.3 Can be used universally on load-bearing mineral substrates and old plasters of mortar groups CS II, CS III and CS IV, synthetic resin-bonded paints and plasters in interior and exterior areas.
KEIM Turado 0.3 is suitable for covering and levelling load-bearing old plasters or paints in layer thicknesses per layer up to approx. 5 mm, as an embedding mortar for fabric reinforcement (e.g. with KEIM glass fibre mesh mat) for smaller surfaces.
Not suitable:
substrates with salt efflorescences; plasto-elastic coatings; saponifiable existing substrates; horizontal and inclined surfaces exposed to weathering

3. PRODUCT PROPERTIES

- very good adhesion
- permeable
- very good stability
- universally applicable
- for interior and exterior use
- good application properties
- very easy to smoothen
- fire behaviour: non-flammable (A1)

MATERIAL CHARACTERISTICS:

– Maximum grain size	0.3 mm

CLASSIFICATION:

– Water absorption class	W2
– Standard Water absorption	DIN EN 1015-18
– Thermal conductivity λ10,dry,mat for P=50%	0.53 W/(mK)
– Thermal conductivity λ10,dry,mat for P=90%	0.58 W/(mK)
– Thermal conductivity Table value according to	DIN EN 1745
– Water vapour diffusion resistance value (μ-value)	≤ 15
– Compressive strength category	CS III (3,5 – 7,5 N/mm²)
– Adhesive tensile strength	≥ 0,2 N/mm²
– Standard Adhesive tensile strength	DIN EN 1015-12

– Fracture pattern Adhesive tensile strength	A B
– Classification according to	DIN EN 998-1
– Plaster type	GP

4. APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION:
The substrate must be level, dry, sound, sufficiently absorbent and free from residues that impair adhesion; it must not be excessively absorbent. Separating substances, such as formwork oil residues on concrete surfaces, must be removed using suitable methods. Severe unevenness must first be levelled using a suitable material of the same type.

Non-suitable substrates:
substrates with salt efflorescences; plasto-elastic coatings; saponifiable existing substrates; horizontal and inclined surfaces exposed to weathering

APPLICATION CONDITIONS:
Ensure the ambient and substrate temperatures are ≥ 5 °C during application and drying. Do not apply in direct sunlight or onto substrates heated by the sun. Protect surfaces from direct sunlight, wind and rain during and after application.

PREPARATION OF MATERIAL / MIXING & CONVEYING:
Mix KEIM Turado 0.3 with approx. 7.0 L - 7.25 L (specification per bag) of clean water with a power stirrer to a stiff-plastic consistency without lumps and allow to mature briefly. Do not remix already stiffened material with water. Application can be performed by hand, via continuous mixer or rendering machine.

CONSUMPTION:
approx. 1,35 kg/m² per mm
The information on material consumption is a guide for smooth substrates. Exact consumption figures must be determined by carrying out test areas.

PROCESSING:
Apply mixed KEIM Turado 0.3 quickly with suitable tools in uniform layer thickness.

LAYERING SYSTEM:
Application in one or several layers, min. 3 mm and max. 5 mm layer thickness per layer. If greater layer thicknesses are required, it is recommended to use KEIM Turado 1.0 in advance and to apply the finishing render layer with KEIM Turado 0.3.

MOISTURE PROTECTION:

TOP COAT:
When using KEIM Turado 0.3 as a finishing coat, the surface may be textured with a sponge board once it has set sufficiently. Free-form texturing or washing in is also possible.

POST-TREATMENT:
KEIM Turado 0.3 must be protected from excessive water loss due to sun or wind and kept moist if necessary.

FINISHING:
Allow to stand before applying a coat.

SERVICE LIFE:
At least 1 day per mm of plaster thickness (depending on temperature and relative humidity). When used as a finishing plaster, allow at least 5 days' curing time before painting. (If the standard rule of 1 day per mm results in longer curing times due to the thickness of the layer, the longer curing time must also be observed before painting).

CLEANING OF TOOLS:
Clean tools, machines and mixers immediatley after use with water. In hardened state only a mechanical removal is possible.

5. PACKAGING

Container content	Unit of measure	Quantity on pallet	Type of container
25	kg	42	bag

6. STORAGE

Maximum storage time	Storage conditions
12 months	dry

7. DISPOSAL

For disposal information refer to section 13 of the safety data sheet.

Waste code: 17 01 01

8. SAFETY INSTRUCTIONS

Refer to the safety data sheet.

GIS code: ZP 1

9. GENERAL INFORMATION

Cover surfaces not to be treated, particularly glass, ceramics and natural stone. Splashes on surrounding surfaces or traffic areas must be immediately diluted with plenty of water and removed.
Mixing with products from other systems or other external additives is not permitted.

10. CERTIFICATES & QUALITY SEALS



The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.

KEIMFARBEN GMBH
Keimstraße 16 / 86420 Diedorf / Tel. +49 821 4802-0
Frederik-Ipsen-Straße 6 / 15926 Luckau / Tel. +49 35456 676-0
www.keim.com / info@keimfarben.de